

Appearance & Shape: To be free from any defect such as flow, burrs, unevenness etc, As per IEC standards. Effective Parameters irrespective of material grade (per piece)

- Effective Length ( $L_e$ ): 76.0 mm
- Effective Area ( $A_e$ ): 82.6mm<sup>2</sup>
- Effective Area ( $A_{Min}$ ): 82.6mm<sup>2</sup>
- Effective Volume ( $V_e$ ): 6281mm<sup>3</sup>  
Approximate weight : 31.75g/pc



## T3113 OL (Un- Coated)

Test Conditions: 10kHz/150mV/CFR COIL,N=01/Lo=Zero/25°C

Material Grade	Initial Permeability ( $\mu_{iac}$ )	AL Value (nH)
CF196	2000 $\pm$ 20%	2700+30%/-20%
CF139	2100 $\pm$ 20%	2900+30%/-20%
CF130	3000 $\pm$ 20%	4100+30%/-20%
CF195A	5000 $\pm$ 20%	6800+30%/-20%
CF265	5000 $\pm$ 20%	6800+30%/-20%
CF190	6000 $\pm$ 20%	8200+30%/-20%
<b>CF197</b>	<b>7000 <math>\pm</math>20%</b>	<b>9500+30%/-20%</b>
CF199	9000 $\pm$ 20%	12200 $\pm$ 30%

## Dimensions(Un-coated Core)

Dimension	Nominal (in mm)	Maximum (in mm)	Minimum (in mm)
A	31.0	31.8	30.5
B	19.0	19.6	18.4
C	13.0	13.5	12.5

